

# MIXTOP SL

## Cementitious self leveling system

---

**Mixtop SL** is a cementitious self leveling system used for leveling uneven floor prior to installation of floor finishes like PVC tiles, vinyl tiles, carpets, etc.

### Appropriation

Mixtop SL provides a self leveling / smoothing underlay for floor finishes like PVC tiles, vinyl sheeting, linoleum on concrete and prefab floors

### Characteristics

Smoothing and self leveling  
Quick drying, easy to use  
Can be troweled to get a smooth finish  
Premixed only addition of water is required at site

### Technical Data & Properties

Standard confirms: BS 890, IP 11/84  
Appearance: Grey powder  
Plastic density (approx): 1.5  
Foot traffic: 15 to 25 hrs at 20 °C  
Foot traffic: 11to18 hrs at 35 °C

### Product Management

**Surface preparation:** The floor to be treated must be clean, free from dust, any loose material, excess laitance, oil, grease etc. Porous surface should be dampened with water and primed with acrylic primer (Mixbond AC diluted). In hot conditions the area should be moistened prior to application. New concrete should be cured for at least two weeks before receiving Mixtop SL

**Application:** Add 5 to 5.5 litre of cool water to 25 kg of powder & mix with electric drill fitted with a spiral mixer to obtain a uniform & lump free consistency. Pour the mixed material over the area and spread at desired thickness using a notched trowel or spiked roller. This material is recommended for a maximum thickness of 8mm

**Curing:** This product does not require curing. But it should be protected from direct sunlight and heavy wind. Do not apply in a highly ventilated area, as the mixed water will evaporate immediately before it cures

**Toppings:** Possible toppings are Neoprene, Vinyl or Acrylic and Resin based material

**Cleaning:** Clean al the tools with water

**Coverage:** 2 to 3 kg/m<sup>2</sup> at 1mm thickness

### Packing & Storage

Mixtop SL is available in 25 Kg bag. For site installations or mass consumptions, deliveries shall be made in bulk custom-designed containers/ storage silos. Mixtop SL should be stored in cool, dry and shaded warehouses. Shelf life is 12 months when stored under cover, out of direct sunlight, protected from extreme temperatures and as per recommendations. In extreme tropical climate, the product must be stored in cooled ambience. Excessive humidity and over exposure to UV will result in the reduction of shelf life.

# MIXTOP SL

Cementitious self leveling system

---

## Health & Safety

As with all construction chemical products, caution should always be exercised. Protective clothing such as gloves and goggles shall be worn whilst handling. Wearing long sleeve overall, safety shoes and face mask is recommended for maximum safety. Reseal all containers after use and ensure product is stored as instructed on the safety section of the labeling. Avoid inhaling the product as it could result in irritations in the respiratory system. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately. Ensure the container is available for the medical attendant to examine any relevant instructions and contents details. For more details, please refer to the MSDS released on each Fab product

Rev. Nov-10/01

THE CONSTRUCTION CHEMIST

Technical information given in this datasheet is true and exact to the best of our knowledge, laboratory upshot and hands-on application. The datasheets of all products are revised/updated regularly and hence ensure that the latest release is used for reference and recommendation. The date of the publishing is as in this sheet. All data are mean of numerous tests, assessment and analysis conducted under laboratory ambience. Climatic disparity in temperature, humidity, etc. and porosity of substrate may impinge on the values.

### Group Head office:

PYCHEM Co. L L C  
Post Box 23940, Sharjah.  
Te: +971 6 5420414 / 5431636  
Fax: +971 6 5421446  
Mail: [mail@fab-cc.com](mailto:mail@fab-cc.com)  
[fabchem@gmail.com](mailto:fabchem@gmail.com)

Under Technical Collaboration with  
**MIX UK Limited**  
Cherry Tree House, Cherry Tree Lane  
Rostherne, Cheshire, WA143RZ  
Web: [www.mixuk.com](http://www.mixuk.com)

### Head office:

T33A/1, Thryambhava Houses  
Kalapetty road, Coimbatore – 14  
Tel: 0422 3222245  
Fax: 0422 2625207  
Mail: [mail@fab-cc.com](mailto:mail@fab-cc.com)  
[fabchem@gmail.com](mailto:fabchem@gmail.com)



FABCHEM



PYCHEM



MIX UK LTD