

MIXTILE MTA

Cementitious polymer modified water resistant tile adhesive

Mixtile MTA is cement based polymer modified water resistant tile adhesive for the thin or thick bed fixing of almost all types of tiles, such as ceramic wall and floor tiles, terrazzo, quarry, marbles and sand stones

Appropriation

Ceramic
Terrazzo
Quarry
Marbles
Sand stones
Wall & Floor tiles

Characteristics

Thin or thick bed fixing
Excellent adhesion to many substrates
Waterproof – permanent immersion does not effect adhesion

Technical Data and Properties

Properties
Can be used for external and internal purposes
Excellent bonding even in damp conditions
Excellent resistance to water and humidity
Slump resistance
Easy and economical to use
Good pot life
Aspect: Powder
Color: Grey / White
Density: 1.8gm / c.c. app
Flash point: Not applicable
Std. conforms to: BS 5980-1980, (DIN EN 12004-2001)
ANSI A. 118.4 – when mixed with Mixtile latex

Product Management

Coverage:
Solid bed fixing: 3mm-6mm depth @ 5.5-11kg/m²
Notch trowel: smooth surface @2kg/m²

Instructions for use: Mixtile MTA adhesive in a ratio of approx. 6 to 7 liters of water per 25kgs bag and 4.8 to 5.2ltr for 20kg bag. Mix to a uniform lump-free consistency. Leave for approximately 5 minutes to allow the resins to completely dissolve. Moisten the support if necessary, but never the tiles. Mixing should be by a force action mixer. Hand mixing is recommended for small quantities only.

Point to be noted: The open curing time of tile adhesive at 30⁰c is approximately 30 minutes. Therefore care should be taken in preparing the mortar. Prepare only the surface, which can be tiled within this time. Mixtile MTA adhesive should not be used on painted or metal surface.

Method of Application: Apply Mixtile MTA adhesive to a uniform thickness of 3mm to 6mm on the support to cover the slots on the back of the tiles, of an area of not more than 1m² at a time.

For horizontal applications a solid bed fixing is recommended as well as for heavy-duty vertical applications.

For other vertical applications, use a toothed spatula to comb horizontally to remove excess. The trowel should have 6mm notches at 25mm intervals center to center.

Apply the tiles, press it, and smooth out carefully so that the mortar is spread evenly. If the bonding is perfect, the tile will not slide. The joints can be filled with Mixgrout (available in gray, white or matching colors on request)

MIXTILE MTA

Cementitious polymer modified water resistant tile adhesive

Consumption

Approximately 2kg/m² depending on the support. Clean the tools with water after use. Store in dry conditions and protect against wind and rain.

Packing and Storage

Shelf life: Mixtile MTA adhesive can be kept for 12 months in unopened packs.

Packing

25kg bag (Grey)

20kg bags (White)

Health and Safety

Mixtile MTA contains no hazardous substances; however it should not be allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles whilst handling. When in contact with the skin and eyes, wash thoroughly and immediately with warm water. If swallowed seek medical attention. For more details, please refer to the MSDS released on each Fab product

Rev. Mar-10/01

FAB

THE CONSTRUCTION CHEMIST

Technical information given in this datasheet is true and exact to the best of our knowledge, laboratory upshot and hands-on application. The datasheets of all products are revised/updated regularly and hence ensure that the latest release is used for reference and recommendation. The date of the publishing is as in this sheet. All data are mean of numerous tests, assessment and analysis conducted under laboratory ambiance. Climatic disparity in temperature, humidity, etc. and porosity of substrate may impinge on the values.

Group Head office:

PYCHEM Co. L L C
Post Box 23940, Sharjah.
Te: +971 6 5420414 / 5431636
Fax: +971 6 5421446
Mail: mail@fab-cc.com
fabchem@gmail.com

Under Technical Collaboration with
MIX UK Limited
Cherry Tree House, Cherry Tree Lane
Rostherne, Cheshire, WA143RZ
Web: www.mixuk.com

Head office:

T33A/1, Thyryambhava Houses
Kalapetty road, Coimbatore – 14
Tel: 0422 3222245
Fax: 0422 2625207
Mail: mail@fab-cc.com
fabchem@gmail.com



FABCHEM



PYCHEM



MIX UK LTD