

MIXBOND PVAPLUS

Bonding agent, admixture for cement and mortar

Mixbond PVAplus is a polyvinyl acetate latex emulsion which is a multipurpose adhesive, surface sealer, admixture and bonding agent. This is a perfect admixture for cement to reinforce its bonding strength and has a wide range of applications

Appropriation

Concrete / mortar admixture
Recommended where permanent dampness occurs
Surface sealer and bitumen primer
Bonding agent for render, repair concrete, floor topping
An effective primer prior to certain decorative coating

Characteristics

Bonding agent for cement screeds, render, mortar and concrete
Used as an integral bonding agent within cementitious system
Reduce water contents and improve adhesion to substrates
Multipurpose application, economical, easy to use
Tenacious adhesive properties
User friendly and quick drying

Technical Data & Properties

Standards conforms: BS 5270
Appearance: White color
Specific gravity: 1.00 at 25 °C
Solid Content: 50%
pH: 6
Chloride content: Nil
Flammability: Non-flammable

Product Management

Dosage rates: Laboratory trials followed by site trials should always be conducted to determine the optimum dosage of Mixbond PVAplus. As a general guide; the following are the dosages under various application situations

Admixture

Mixbond PVAplus improves quality of mortar application, increases the mechanical strength of screeds, reduces shrinkage and has perfect adhesion even on smooth concrete. For maximum bond strength, add Mixbond PVAplus @ 5liters /100kg of cement

Bitumen Primer

Stops bleeding of bitumen coating. Here, the surfaces are primed with Mixbond PVAplus diluted with equal parts of water. This will form an efficient barrier that may be safely topped with most oil-base paints.

Bonding new concrete to old

Mixbond PVAplus ensures that the substrate is stable, sound and thoroughly clean and free from oil, grease and any adhering material. Apply a sealing coat of Mixbond PVAplus diluted with four parts of clean water and allow drying. Apply a bonding coat of Mixbond PVAplus diluted with an equal volume of water and lay the new concrete while this coat is still tacky.

Screed preparation

For thin crack free floor screed (normal to heavy duty), Mixbond PVAplus, 20 litres to 30 litres/100kg cement is recommended as a standard dosage

MIXBOND PVAplus

Bonding agent, admixture for cement and mortar

Application: For uneven surfaces or gaps to be filled, Mixbond PVAplus is diluted with equal amount of water to obtain a paste with plaster, cement or with fine sand. Such paste can be applied as an adhesive for plaster boards, polystyrene tiles etc. to ceiling and walls. If the bonding surface is more porous, add 3 times the amount of water to Mixbond PVAplus and prime the surface

As a bonding agent for screeds, plaster and rendering, the surface should be sound and free from all unwanted materials, such as oil, grease, paint etc. Sealing of the surface is done with 1 part Mixbond PVAplus with 3 parts of water. Then apply the bonding coat (1:1) and render screed or plaster normally. The same method is used to bond new concrete to old.

Do not use below 5^oc

Over trowelling has to be avoided

Always follow the mixing ratio and instructions

Coverage

20 litres to 30 litres/100kgs cement in 140ltr/m² (as an admixture)

Ratio 1:1- 01 litre/20m²

Ratio 1:3 – 01 litre/35m²

Curing occurs within 3 - 7 days.

Packing & Storage

Up to 12 months in manufacturer's sealed containers stored in a cool dry place and away from high temperature. Available in 20kg and 200kg container. Reseal the container after use and ensure product is stored as instructed on the label

Health & Safety

Mixbond PVAplus contains no hazardous substances; however it should not be allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles whilst handling. When in contact with the skin and eyes, wash thoroughly and immediately with warm water. If swallowed seek medical attention. For more details, please refer to the MSDS released on each product

Rev. Nov-10/01

Technical information given in this datasheet is true and exact to the best of our knowledge, laboratory upshot and hands-on application. The datasheets of all products are revised/updated regularly and hence ensure that the latest release is used for reference and recommendation. The date of the publishing is as in this sheet. All data are mean of numerous tests, assessment and analysis conducted under laboratory ambience. Climatic disparity in temperature, humidity, etc. and porosity of substrate may impinge on the values.

Group Head office:

PYCHEM Co. L L C
Post Box 23940, Sharjah.
Te: +971 6 5420414 / 5431636
Fax: +971 6 5421446
Mail: mail@fab-cc.com
pychemco@gmail.com

Under Technical Collaboration with
MIX UK Limited
Cherry Tree House, Cherry Tree Lane
Rostherne, Cheshire, WA143RZ
Web: www.mixuk.com

Head office:

T33A/1, Thryambhava Houses
Kalapetty road, Coimbatore – 14
Tel: 0422 3222245
Fax: 0422 2625207
Mail: mail@fab-cc.com
fabchem@gmail.com

THE CONSTRUCTION CHEMIST



FABCHEM



PYCHEM



MIX UK LTD