

MIXGROUT MG

Cementitious water resistant grout

Mixgrout MG is a fine powder to be mixed with water to obtain a smooth creamy paste for grouting of tiles. It constitutes a water resistant non-shrink finish up to 4mm wide, easily applied creamy paste for clean grouting of tiles, sets to be a decorative water resistant finish.

Appropriation

Mixgrout MG is easily applied by hand and will give a water and weather resistant joint with no shrinkage. It is suitable for filling joints in interior and exterior wall and floor tiles, marbles or granites. Strong bonding properties of Mxgrout MG remains in place permanently without wear.

Characteristics

Water resistant, crack free up to 4mm wide joints.

Basic colours are White and grey, any other colours can be custom designed (Refer Pychem Colour chart)

Ideal for both interior and exterior use.

Technical Data and Properties

Standards: BS 5980-cementitious adhesive and grouts.

Density: 1.8gm/cc

Composition: Mixture of special cement, polymers, fillers and suitable additives.

Fillers: Crushed, precisely graded extenders

Binders: Hydraulic and organic

Product Management

Surface preparation: All Tiles and joints should be securely fixed and thoroughly clean before grouting. Ensure that all tile joints and edges are free of excess tile fixing mortar and other

Application: Apply Mixgrout MG after a minimum of 24 hours from tiling. Apply the grout diagonally into the joints with a rubber edge spatula or squeegee. Remove excess grout with a moist sponge before drying. Do not apply grout to an area that is of a size that cannot be completed within one hour.

Mixing: Mix the powder with clean portable water to obtain a smooth creamy paste, approximately 2 liters of water for 5kg of powder then stand the mixture for 10 minutes prior to use. Mixing should be by a force action mixer.

Hand mixing is recommended for small quantities only. Thorough mixing is strictly required when using colour grouts to get complete dissolve of pigment contents.

Note: for submerged applications add Mixtile Latex additive @0.4ltr / 10kg bag

Coverage

Approx. 1kg of powder is enough to grout 4m² using Std. Tile 15 x 15cm.

Cleaning

Tools should be cleaned with water after use

Packing & Storage

Mixgrout MG is available in 1, 5 & 10kg bags.

Grout can be stored up to 12 months in unopened bags kept in dry conditions out of direct sunlight and rain.

MIXGROUT MG

Cementitious water resistant grout

Health & Safety

Mxgrout MG contains no hazardous substances; however it should not be allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles whilst handling. When in contact with the skin and eyes, wash thoroughly and immediately with warm water. If swallowed seek medical attention. For more details, please refer to the MSDS released on each Fab product

Rev. Mar-10/01

THE CONSTRUCTION CHEMIST

Technical information given in this datasheet is true and exact to the best of our knowledge, laboratory upshot and hands-on application. The datasheets of all products are revised/updated regularly and hence ensure that the latest release is used for reference and recommendation. The date of the publishing is as in this sheet. All data are mean of numerous tests, assessment and analysis conducted under laboratory ambience. Climatic disparity in temperature, humidity, etc. and porosity of substrate may impinge on the values.

Group Head office:

PYCHEM Co. L L C
Post Box 23940, Sharjah.
Te: +971 6 5420414 / 5431636
Fax: +971 6 5421446
Mail: mail@fab-cc.com
fabchem@gmail.com

Under Technical Collaboration with
MIX UK Limited
Cherry Tree House, Cherry Tree Lane
Rostherne, Cheshire, WA143RZ
Web: www.mixuk.com

Head office:

T33A/1, Thyryambhava Houses
Kalapetty road, Coimbatore – 14
Tel: 0422 3222245
Fax: 0422 2625207
Mail: mail@fab-cc.com
fabchem@gmail.com



FABCHEM



PYCHEM



MIX UK LTD